

## Effect of Different Cure Conditions on Compressive Strength of Concrete Having Different Properties

Bahar Kocaman, Recep Yanik, Canan Kose and Adem Ozturk  
Department of Agricultural Structures and Irrigation, Faculty of Agriculture,  
Ataturk University, Erzurum, Turkey

**Abstract:** This research was carried out to determine unit weights and compressive strengths for the concrete samples produced with normal aggregate obtained Erzurum province and lightweight aggregate obtained Van-Ercis province and cured under different conditions. Unit weights of concrete specimens produced with normal aggregate were 2325 under air cure, 2360 under water cure, 2358 kg m<sup>-3</sup> under steam cure. Unit weights of concrete specimens produced with lightweight aggregate were 906 under air cure, 1060 under water cure, 972 kg m<sup>-3</sup> under steam cure. In average, 28 days compressive strength of concrete specimens produced with normal aggregate were 180.3 under air cure, 270.0 under water cure, 240.1 kgf cm<sup>-2</sup> under steam cure. In average 28 days compressive strength of concrete specimens produced with lightweight aggregate were 60.0 under air cure, 45.2 under water cure, 52.4 kgf cm<sup>-2</sup> under steam cure.

**Key words:** Lightweight aggregate, normal aggregate, concrete cure, unit weight, compressive strength, Turkey

### INTRODUCTION

Concrete is a building material formed by mixing aggregates (sand, gravel and crushed stone), cement and water in a suitable ratio and having high strength by hardening at the end of certain time (Ekmekyapar and Orung, 2001). It should be initiated to cure (maintain) and control of concrete with the end of its production. Concrete needs meticulous care in the next days following production. One of the more important effects on compressive strength of concrete is care (cure) type after its production. With different cure practices different strengths is obtained. After production if not concrete subject to damp cure for a long time, shrinkage cracks (fractures) occur (Lea, 1956). Concrete is a building material having high compressive strength like other crispy materials. So, concrete compressive strength is used in reinforced concrete accounts. Standard compressive strength of concrete is the strength of under axial compression specimens, curing in water for 28 days (Neville, 1983).

In addition to normal aggregate being used in concrete production, usage of lightweight aggregate can be an important source for agricultural buildings near rural provinces.

### MATERIALS AND METHODS

In experimental study, normal aggregate provided from sand-gravel bed which Aras river accumulated,

obtained Pasinler and Horasan regions of Erzurum province, lightweight aggregate obtained from Van-Ercis province as binder cement and mixing water used. The chemical analysis results of lightweight aggregate shown in Table 1, chemical analysis results of portland cement shown in Table 2 and physical and mechanical analysis results of portland cement also shown in Table 3.

Tests for specific gravity, water absorption, organic materials, fine materials and determining the amount of sulfate, related to lightweight aggregate made according to ASTM C 332 (Anonymous, 1998a); TS 13055-1/AC (Anonymous, 2006); ASTM C 136-96 (Anonymous, 1998b); ASTM C 29 M-97 (Anonymous, 1998c); ASTM C 127-88 (Anonymous, 1998d); ASTM C 128-97 (Anonymous, 1998e); ASTM C 40-97 (Anonymous, 1998i); ASTM C 142-71 (Anonymous, 1998f); TS EN 1744-1 (Anonymous, 2010b) and TS EN 1097-6/A1 (Anonymous, 2007).

Concrete options produced from the aggregates applied in experimental study research materials, determined by the way that taking into consideration of steam, water and air curing conditions of specimens.

For structural concrete and masonry units concrete produced with mixed aggregate, maximum size of aggregate chosen 16 mm appropriate to the specified value given in TS EN 13055-1/AC (Anonymous, 2006) and ASTM C 331 (Anonymous, 1998g). Cement dosage is a factor creating important properties and effecting economy at large scale of concrete. Conditions for agricultural building taken into

Table 1: Chemical analysis results of lightweight aggregate obtained Van-Ercis province

Chemical components	Ratio (%)
MgO	0.01
Al <sub>2</sub> O <sub>3</sub>	13.20
SiO <sub>2</sub>	71.35
CaO	1.84
Fe <sub>2</sub> O <sub>3</sub>	1.54
SO <sub>3</sub>	0.04
K <sub>2</sub> O	5.00
Na <sub>2</sub> O	3.40
TiO <sub>2</sub>	0.25
Ignition loss	3.37

Table 2: Chemical analysis results of PC 325 cement

Chemical components	Ratio (%)
SiO <sub>2</sub>	17.69
Fe <sub>2</sub> O <sub>3</sub>	3.59
Al <sub>2</sub> O <sub>3</sub>	5.89
CaO	57.69
MgO	3.39
SO <sub>3</sub>	2.57
Ignition loss	2.50
Sulphide (S <sup>-2</sup> )	0.27
Chlorine (Cl)	0.04
Insoluble residue	4.86
Undetermined	0.55
Free CaO	0.96

Table 3: Physical and mechanical properties of cement

Parameters	Values
Specific gravity (g cm <sup>-3</sup> )	3.03
Lightweight (g L <sup>-1</sup> )	1130.00
Specific surface (cm <sup>2</sup> g <sup>-1</sup> )	3613.00
Remainder on 200 µm sieve (%)	0.10
Remainder on 200 µm sieve (%)	3.10
Setting time initial (h)	2:30.00
Setting time final (h)	3.20
Volume expansion (Le Chotelier, mm)	3.00
2 days	12.25
<b>Compressive strength (N mm<sup>-2</sup>) days</b>	
7	24.80
28	36.50

consideration in determining strength levels. Cement dosage changes between 90-200 kg m<sup>-3</sup> range for unreinforced concretes, especially isolation concrete and changes between 300-500 kg m<sup>-3</sup> range for structural concretes (Hammel and Schumacher, 1975). Due to agricultural buildings usually are single storey, it may be required more less strength than the other buildings in their conveyor units. By the way that all these factors taking into consideration, cement dosage chosen 250 kg m<sup>-3</sup>. In the preliminary tests of fresh lightweight concrete specimens, 3-6% air contents was obtained that is appropriate to 4-8% air contents (PCA, 1972; Neville, 1973) which are quite appropriate for the concrete produced with the aggregate having maximum aggregate size as 16 mm. So, it was decided to produce the concrete specimens as pure air.

## RESULTS AND DISCUSSION

As a result of preliminary slump tests for concrete specimens produced with lightweight aggregate; values

ranged between 3-6 cm which appropriate in terms of workability, so slump value was taken 5 cm in all experimental mixtures. Mixture accounts of concretes produced with lightweight aggregate were made based to (according to) TS 2511 (Anonymous, 1977a). This method was also used for the concrete specimens, produced with normal aggregate.

For using in experimental study by making account of mixtures 18 concrete specimens having 250 kg cement dosage were prepared. According to TS EN 12350-2 (Anonymous, 1977b) consistency and according to TS 2941 (Anonymous, 1978a) unit weight of fresh concrete were determined. Specimens produced in shape of cylinder having 15 cm diameter and 30 cm height appropriate to ASTM C 192 ve TS 3323 (Anonymous, 1998h; Anonymous, 1979).

Standard cylinder molds were used for cylinder shaped specimens. After lubricating inside of molds with mineral oil, concrete placed into molds, after sweeping 75 times then surface of concrete specimens levelled with a steel trowel (spatula). To prevent the moisture loss of concrete specimens, upper sides covered with plastic bags and were kept in molds for 24 h (Anonymous, 1978b).

After removing from the molds, concrete specimens were left to cure conditions then at the 28th day they were subjected to tests (Anonymous, 1978c). According to TS 3624 (Anonymous, 1981) unit weights according to TS EN 12390-3 (Anonymous, 2010a) compressive strength of 28 days aged concrete specimens were determined.

Theoretical fresh unit weight values of lightweight concretes were found as 1080-1547 kg m<sup>-3</sup> and real fresh unit weights of them were found as 1150 kg m<sup>-3</sup>. Theoretical fresh unit weights of normal concrete were found as 2189-2218 kg m<sup>-3</sup> and real fresh unit weights of normal concretes were found as 2275 kg m<sup>-3</sup>. Total 28 days air-dried unit weights of hardened concretes were found between 960-1060 kg m<sup>-3</sup> for the specimens produced with lightweight aggregates obtained Van-Ercis province and between 2325-2358 kg m<sup>-3</sup> for the specimens produced with normal aggregates.

Unit weights increased depending on humidity increase in the cure environment. When 28 days average compressive strength examined; it is seemed that maximum compressive strength value for lightweight concrete were obtained from air-cured specimen and that of lightweight concrete were obtained from water-cured specimen. The values of 28 days compressive strength and average unit weight for concrete specimens are shown in Table 4. As showed in Table 4 for lightweight concretes, compressive strength decreased with

Table 4: Average unit weight and 28 days compressive strength values of concrete specimens

Parameters	Normal aggregate Cure type			Lightweight aggregate Cure type		
	Air	Water	Steam	Air	Water	Steam
Unit weight (kg m <sup>-3</sup> )	2325	2360	2358	906	1060	972
Compressive strength (kg cm <sup>-2</sup> )	180.3	270	240.1	60.0	45.2	52.4

the increase in cure environment humidity for normal concretes compressive strength increased with the increase in cure environment humidity.

### CONCLUSION

Results showed that one of the most important factor effecting concrete compressive strength is curing conditions. Compressive strengths of concretes produced with normal aggregate lower than that of concrete produced with lightweight aggregate. In addition to concretes having inappropriate mixtures, concretes having appropriate mixtures but without having enough cure also have effects at important level on low compressive strength.

### REFERENCES

Anonymous, 1977a. TS 2511: Mix design for structural lightweight aggregate concrete. Turkish Standards Institution, Ankara, Turkey.

Anonymous, 1977b. TS EN 12350-2: Testing fresh concrete, Part 2: Slump test. Turkish Standards Institution, Ankara, Turkey.

Anonymous, 1978a. TS 2941: Determination of unit weight, yield and air content of fresh concrete by weighting procedure. Turkish Standards Institution, Ankara, Turkey.

Anonymous, 1978b. TS 3068: Making and curing concrete test specimens in the laboratory. Turkish Standards Institution, Ankara, Turkey.

Anonymous, 1978c. TS 3244: Cure of concrete specimens. Turkish Standards Institution, Ankara, Turkey.

Anonymous, 1979. TS 3323: The method of making accelerated curing and testing of concrete compression test specimens. Turkish Standards Institution, Ankara, Turkey.

Anonymous, 1981. TS 3624: Test method for determination the specific gravity the absorption water and the void ratio in hardened concrete. Turkish Standards Institution, Ankara, Turkey.

Anonymous, 1998a. ASTM C 332: Specification for lightweight aggregates for insulating concrete. ASTM Standards Designation, C 332-87,04.01, 200-202. <http://www.astm.org/Standards/C332.htm>.

Anonymous, 1998b. ASTM C 136-96: Test method for sieve analysis of fine and coarse aggregates. Annual Books of ASTM Standards Designation, C 136-96,04.01, pp: 74-82.

Anonymous, 1998c. ASTM C 29 M-09: Test method for unit weight and voids in aggregate. Annual Books of ASTM Standards Designation, C 29 M-09,04.01, pp: 1-4. URL: <http://www.astm.org/Standards/C29.htm>.

Anonymous, 1998d. ASTM C 127-88: Test method for specific gravity and absorption of coarse aggregate. Annual Books of ASTM Standards Designation, C 127-88,04.01, pp: 64-68. <http://www.astm.org>.

Anonymous, 1998e. ASTM C 128-97: Test method for specific gravity and absorption of fine aggregate. Annual Books of ASTM Standards Designation, C 128-97,04.01, pp: 69-72.

Anonymous, 1998f. ASTM C 142-71: Test method for clay lumps and friable particles in aggregates. Annual Books of ASTM Standards Designation, C 142-71,04.01, pp: 94-95. <http://www.astm.org>.

Anonymous, 1998g. ASTM C 331: Specification for lightweight aggregates for structural concrete. Masonry Units. Annual Books of ASTM Standards Designation, C 331-98, 04.01, pp: 197-199.

Anonymous, 1998h. ASTM C 192: Practice for making and curing concrete test specimens in the laboratory. Annual Books of ASTM Standards Designation, C 192/C 192 M. 95, pp: 112-119. <http://www.astm.org>.

Anonymous, 1998i. ASTM C 40-97: Test method for organic impurities in fine aggregates for concrete. Annual Books of ASTM Standards Designation, C 40-97,04.01, pp: 22-23, <http://www.astm.org>.

Anonymous, 2006. TS 13055-1/AC: Lightweight aggregates, Part 1: Lightweight aggregates for concrete. Mortar and Grout. Turkish Standards Institution, Ankara, Turkey.

Anonymous, 2007. TS EN 1097-6/A1: Tests for mechanical and physical properties of aggregates, Part 6: Determination of particle density and water absorption. Turkish Standards Institution, Ankara, Turkey.

Anonymous, 2010a. TS EN 12390-3: Testing hardened concrete, Part 3: Compressive strength of test specimens. Turkish Standards Institution, Ankara, Turkey.

Anonymous, 2010b. TS EN 1744-1: Tests for chemical properties of aggregates, Part 1: Chemical analysis. Turkish Standards Institution, Ankara, Turkey.

Ekmekyapar, T. and I. Orung, 2001. Knowledge of structural materials. Ataturk University Agricultural Faculty, Publications No. 145, Erzurum, Turkey.

Hammel, A. and W. Schumacher, 1975. Concrete. Kalender Technical Publisher, Istanbul, Turkey.

Lea, F.M., 1956. The Chemistry of Cement and Concrete 3rd Edn., S. Edward Arnold Ltd., London, UK.  
Neville, A.M., 1973. Properties of Concrete. John Wiley and Sons, New York, USA.

Neville, A.M., 1983. Properties of Concrete. Halsted Press, New York, USA.  
PCA, 1972. Structural lightweight concrete portland cement association, concrete information, revised Chapter 13. Design and Control of Concrete Mixtures, Skokie.